

T S1/5/1

1/5/1

DIALOG(R)File 351:Derwent WPI

(c) 2002 Thomson Derwent. All rts. reserv.

012115270

WPI Acc No: 1998-532182/199845

XRAM Acc No: C98-159792

XRPX Acc No: N98-415191

Optical system for integrated circuit manufacture - comprises one crystalline optical member and amorphous optical member made of synthetic quartz glass

Patent Assignee: HERAEUS QUARZGLAS GMBH & CO KG (HERA); SHINETSU QUARTZ PROD CO LTD (SHIN-N); HERAEUS QUARZGLAS GMBH (HERA); SHINETSU SEKIEI KK (SHIN-N); FUJINOKI A (FUJI-I); NISHIMURA H (NISH-I)

Inventor: FUJINOKI A; NISHIMURA H

Number of Countries: 019 Number of Patents: 007

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
WO 9843135	A1	19981001	WO 98EP1692	A	19980323	199845 B
JP 10270351	A	19981009	JP 9790232	A	19970325	199851
JP 10270352	A	19981009	JP 9790235	A	19970325	199851
EP 901650	A1	19990317	EP 98912497	A	19980323	199915
			WO 98EP1692	A	19980323	
EP 901650	B1	20010919	EP 98912497	A	19980323	200155
			WO 98EP1692	A	19980323	
US 20010030798	A1	20011018	WO 98EP1692	A	19980323	200166
			US 98194536	A	19981125	
DE 69801731	E	20011025	DE 601731	A	19980323	200171
			EP 98912497	A	19980323	
			WO 98EP1692	A	19980323	

Priority Applications (No Type Date): JP 9790235 A 19970325; JP 9790232 A 19970325

Patent Details:

Patent No	Kind	Lan	Pg	Main IPC	Filing Notes
-----------	------	-----	----	----------	--------------

WO 9843135	A1	E	27	G03F-007/20	
------------	----	---	----	-------------	--

Designated States (National): US

Designated States (Regional): AT BE CH DE DK ES FI FR GB GR IE IT LU MC NL PT SE

JP 10270351	A		8	H01L-021/027	
-------------	---	--	---	--------------	--

JP 10270352	A		8	H01L-021/027	
-------------	---	--	---	--------------	--

EP 901650	A1	E		G03F-007/20	Based on patent WO 9843135
-----------	----	---	--	-------------	----------------------------

Designated States (Regional): DE FR GB IT NL

EP 901650	B1	E		G03F-007/20	Based on patent WO 9843135
-----------	----	---	--	-------------	----------------------------

Designated States (Regional): DE FR GB IT NL

US 20010030798	A1			G02B-001/00	
----------------	----	--	--	-------------	--

DE 69801731	E			G03F-007/20	Based on patent EP 901650
-------------	---	--	--	-------------	---------------------------

Based on patent WO 9843135

Abstract (Basic): WO 9843135 A

An optical system for integrated circuit fabrication, where an integrated circuit pattern image is projected on a wafer using an excimer laser emitting UV laser light of short wavelength comprises of, at least one crystalline optical member made of a single crystal fluorite and at least one amorphous optical member made of synthetic quartz glass. The crystalline optical member is disposed in a 1st position closest to an exposing surface of a wafer and/or a pupil plane, which is a position through which the laser light is transmitted

at a relatively high light energy density g (mJ/cm²), and the amorphous optical member is disposed in a 2nd position remote from exposing surface of a wafer and/or the pupil plane, which is a position through which the laser light is transmitted at a relatively low light energy density, g (mJ/cm²) and whereby the amorphous optical member is made of quartz glass having a hydrogen molecule concn. in the range of 1×10^6 to 5×10^{18} molecules/cm³.

USE - For fabricating integrated circuits.

Dwg.0/4

Title Terms: OPTICAL; SYSTEM; INTEGRATE; CIRCUIT; MANUFACTURE; COMPRISE;
ONE; CRYSTAL; OPTICAL; MEMBER; AMORPHOUS; OPTICAL; MEMBER; MADE;
SYNTHETIC; QUARTZ; GLASS

Derwent Class: L03; P81; P84

International Patent Class (Main): G02B-001/00; G03F-007/20; H01L-021/027

International Patent Class (Additional): C03C-003/06; G02B-001/02;

G02B-013/24

File Segment: CPI; EngPI

?

**OPTICAL SYSTEM
FOR INTEGRATED CIRCUIT FABRICATION**

Detailed Description of the Invention

Field of Industrial Application

The present invention relates to an optical system for fabrication of an integrated circuit of a capacity of 64 M bits to 254 M bits. More particularly, the present invention relates to an optical system for fabrication of an integrated circuit in which an integrated circuit pattern image is projected on a wafer using ultraviolet laser light of a short wavelength having a narrowed spectral band width with the help of an optical system made of quartz glass material.

Prior art

Heretofore, an optical photolithographic technique, in which a pattern formed on a mask is transferred onto a wafer by illumination, has widely been used as an optical system for fabrication of an integrated circuit, owing to its advantage in cost compared with other techniques, such as those using an electron beam, an X-ray or the like.

While a projection aligner has been developed in a conventional photolithographic technique, said projection aligner using an H-line light of a wavelength of 365 nm emitted from a high pressure mercury lamp for depicting a patterned image with a line width of 0.5 to 0.4 μm , such an projection aligner corresponds to an integrated circuit (IC) of a capacity of 16 M bits to or less.

C
CONFIRMATION COPY

An IC of 64 M bits to 256 M bits of the first generation requires a resolution of 0.25 to 0.35 μm and an IC of 1 G bits requires a resolution of 0.13 to 0.20 μm . A resolution of 0.35 μm is not achieved by a wavelength of an I-line light and therefore, KrF light is used as a light source. In a region of a resolution better than 0.2 μm , ArF light is used instead of KrF light, especially an ArF excimer laser is used as a light source.

There are various problems in an photolithographic technique using an ArF excimer laser and one of them is a problem associated with an optical material constituting lenses, mirrors and prisms, which constructs an optical system for projection.

While an optical material which shows a good transmittance in a wavelength of 193 nm emitted from an ArF laser is substantially limited to quartz glass, especially high purity synthetic quartz glass, ArF light adversely affects quartz glass to give a damage ten times or more as large as KrF light does.

An improved resistance to excimer laser irradiation of quartz glass is dependent on a hydrogen concentration contained therein, as described in EP-A 401 845. According to the publication, there is disclosed that quartz glass constructing an optical system of a projection aligner using a KrF excimer laser as a light source was able to secure an enough resistance to the laser light with a hydrogen concentration of 5×10^{16} molecules/cm³ or more contained therein.

However, since an influence exerted on quartz glass by ArF laser light is extremely greater, compared with KrF laser light, as has been described above, it was found from an investigation into a degree of the damage, such as changes in a transmittance and a refractive index thereof, produced in the bulk of synthetic quartz glass that required hydrogen concentration for preventing occurrence of the damage is 100 to 1000 times or more as large as the hydrogen molecule concentration required in the case of a KrF excimer laser light, in a concrete manner 5×10^{18} molecules/cm³ or more.

There are two methods to make synthetic quartz glass incorporated with hydrogen molecules. In one of the methods, wherein hydrogen molecules are incorporated into the synthetic quartz glass in atmospheric pressure, adjusting the environment in production, the maximum concentration of hydrogen molecule to be incorporated, is on the order of 5×10^{16} molecules/cm³. In the other method, wherein hydrogen molecules are incorporated into the quartz glass by a heat treatment in a pressured hydrogen atmosphere, the upper limit of an incorporated hydrogen molecule concentration is the same 5×10^{18} molecules/cm³ under a

pressure of 10 atm as well, when the pressure is its maximum under Japanese Law of High Pressure Gas Control.

In such circumstances, if a hydrogen molecule concentration of 5×10^{18} molecules/cm³ or more is desired, it is required that quartz glass is subjected to a heat treatment at a temperature of 1000°C or higher and in a high-pressure hydrogen atmosphere of 100 atm or higher as described in EP-A 483 752.

Problems the Invention Seeks to Solve

However, since a heat treatment at 1000 °C or higher under a pressure of 100 atm or higher provokes new defects in the bulk of quartz glass, a temperature of the heat treatment preferably is in the range of 200 to 800 °C (see Publication of Unexamined Japanese Patent Application No. Hei 6-166528). In the case where a great number of hydrogen molecules, which is 5×10^{18} molecules/cm³, are incorporated into quartz glass by a heat treatment at a temperature in this range in a hydrogen atmosphere, there arises a fault that it takes very long to incorporate hydrogen molecules in the quartz glass to such a concentration, since a diffusion coefficient of a hydrogen molecule is not so large and in addition, to conduct a heat treatment in a high pressure atmosphere results in not only decrease of homogeneity in refractive index in the bulk of the quartz glass but also generation of strains in the bulk.

Therefore, if quartz glass is subjected to a high-pressure, high-temperature treatment, as a result another heat treatment becomes necessary for readjustment. These treatments make the process to produce quartz glass which is suitable for constituting an optical system of a projection aligner industrially very complex and time-consuming, which in turn makes the quartz glass having a hydrogen concentration of 5×10^{18} molecules/cm³ or more, a homogeneity in refractive index, a low level of strains and the like highly expensive.

However even if the quartz glass having hydrogen concentration of 5×10^{18} molecules/cm³ or more, optical properties, such as a homogeneity in refractive index, a low level of strains and the like, is obtained, a volume constriction causing a change in refractive index of the quartz glass may arise during irradiation by ArF laser light.

It is an object of the present invention to provide an optical system for use with ultraviolet light of a short wavelength with a narrowed spectral band width, especially ArF laser light, as

illumination in the projection aligner without degrading properties such as durability, optical transmittance and the like with a low cost and ease as a whole.

Means to Solve the Problem

The present invention focuses its attention to the following points.

As mentioned above, it is industrially very complex, requires a long time of treatment and makes production difficult and very expensive, to incorporate hydrogen molecules in optical members constituting an optical system for exposure using illumination of ArF laser light at a concentration of 5×10^{18} molecules/cm³ in order to improve durability of the optical system during exposure.

Accordingly, the present invention has a gist to constitute the optical system by combination of synthetic quartz glass and fluorite.

A technique to combine synthetic quartz and fluorite in an optical system used for integrated circuit fabrication has been disclosed in Publication of Unexamined Japanese Patent Application No. Hei 8-78319 (hereinafter referred to as first prior art technique), but the technical concept is essentially different from that of the present invention.

The first prior art technique is to constitute the optical system for exposure with a diffraction optical element having a positive power, a quartz lens having a negative power and a fluorite lens having a positive power, which constitution is to correct a chromatic aberration. In the first prior technique, the chromatic aberration is corrected by a combination of a diffraction optical element and a refracting lens respectively having positive and negative powers, and a fluorite having a positive power, wherein a combination of optical elements, different from one another in optical dispersion corrects chromatic aberration. Such a combination specially realizes an optical system having an image formation property that a secondary spectrum of chromatic aberration is minor and thereby not only can a larger curvature radius of a lens, a larger NA, a larger field of view be realized to give room to improvement on a specification of the optical system but a tolerance of eccentricity in fabrication is also larger to promote easy fabrication.

Therefore, since the prior art technique is one in which a quartz glass lens having a negative power and a fluorite lens having a positive power are combined from the view point of solving problems in design and fabrication, it is different from the present invention in that the present invention has the object to prevent degradation in resistance to laser light caused by high

output irradiation. Therefore, the prior art is also confirmed to be different in constitution on the basis of the different objects, as mentioned above.

In order to improve resistance to laser light, according to a first aspect of the present invention, an optical system comprises a combination of optical members made of synthetic quartz glass and fluorite, wherein: a crystalline optical member, which is located in a position through which laser light is transmitted at a relatively high light energy density ϵ (mJ/cm²) (hereinafter referred to as wafer side optical member), is made of fluorite to avoid itself to be broken under irradiation of ArF laser light; and an amorphous optical member, which is located in a position through which laser light is transmitted at a relatively low light energy density ϵ (mJ/cm²) (hereinafter referred to as light source side optical member), is made of synthetic quartz glass having a hydrogen molecule concentration in the range of 1×10^{17} molecules/cm³ to 5×10^{18} molecules/cm³.

The relative low hydrogen content of the quartz glass of the amorphous optical member can be simply achieved by doping the quartz glass in atmospheric pressure. As a result it is more easy to establish a high quality of the optical properties of the quartz glass, especially to attach importance to homogeneity of refractive index. The entire optical system achieves high transmittance.

More preferably, the optical system comprises optical members made of a plurality of qualities of synthetic quartz glass and an optical member made of a kind of fluorite, wherein the fluorite has a homogeneity of refractive index Δn of 3×10^{-6} /cm or less and a birefringence of 2 nm/cm or less; a first quality of synthetic quartz glass has a hydrogen molecule concentration in the range of 5×10^{17} molecules/cm³ to 5×10^{18} molecules/cm³, a homogeneity of refractive index Δn of 2×10^{-6} /cm or less and a birefringence of 1 nm/cm or less; and a second quality of synthetic quartz glass has a hydrogen molecule concentration in the range of 1×10^{17} molecules/cm³ to 5×10^{18} molecules/cm³, a homogeneity of refractive index Δn of 2×10^{-6} /cm or less and a birefringence of 1 nm/cm or less.

That is, while according to the present invention, in a high energy level region of laser light, fluorite having resistance to a change in transmittance of laser light, especially single crystal fluorite due to absolutely no volume constriction over time is observed instead of quartz glass, it is extremely difficult to achieve such optical properties as homogeneity in refractive index, low birefringence and the like for a large diameter optical member used in photolithography when fluorite is used as the material.

If synthetic quartz glass capable of being doped under atmospheric pressure and having high homogeneity is used in a low energy level region of laser light, resistance to a change in transmittance and high homogeneity can be maintained in the entire optical system.

As a relation between fluorite and synthetic quartz glass in terms of a measure of homogeneity such as a refractive index Δn or a birefringence nm/cm, it is preferred that the homogeneity is set better in the synthetic quartz glass used as an amorphous optical member than in the fluorite used as a crystalline optical member, in other words, a measure of homogeneity is set better in a light source side-optical member than a wafer side-optical member. In a more definite manner, it is preferred that a wafer side-optical member is of single crystal and has a homogeneity of refractive index Δn of $3 \times 10^{-8}/\text{cm}$ or less and a birefringence of 2 nm/cm or less, and a light source side-optical member is of synthetic quartz glass and has a homogeneity of refractive index Δn of $2 \times 10^{-8}/\text{cm}$ or less and a birefringence of 1 nm/cm or less.

Generally, excimer laser light has a spread in oscillating wavelength and accordingly, unless the spread in oscillating wavelength is restricted to a narrow band width in a monochromatic lens system, a material of whose constituent lenses is only quartz, chromatic aberration arises. Therefore the present invention employs an ArF excimer laser light which is ultraviolet light of a short wavelength having an oscillating wavelength width of 1.5 pm or less (FWHM or full width at half maximum).

The fluorite used as an optical member can secure an internal transmittance per cm of about 98 %/cm after irradiation of the pulsed laser light having a wavelength of 193 nm at an energy density per pulse of 50 mJ/cm² for a pulse count of 1×10^6 .

In order to improve resistance to laser light, according to a further aspect of the present invention, an optical system for circuit pattern exposure of ArF excimer laser light having a wavelength of 193 nm is provided, wherein the average transmittance of the optical system as a whole is about 98.0 %/cm or more, the transmittance of the at least one amorphous optical member is 99.5 %/cm or more and the transmittance for the crystalline optical member is 99.8 %/cm or more, whereby at least one amorphous optical member belonging to the second quality is disposed in a region through which the laser light is transmitted at an energy density of $\leq 0.1 \text{ mJ/cm}^2$, and at least one amorphous optical member belonging to the first quality is disposed in a region, through which the laser light is transmitted at an energy density of

$0.1 < \epsilon < 0.4 \text{ mJ/cm}^2$, and the at least one crystalline optical member is disposed in a region, through which the laser light is transmitted at an energy density of $\epsilon \geq 0.4 \text{ mJ/cm}^2$.

Besides, in order to achieve homogeneity in refractive index in the entire optical system and more particularly, maintain a change in the average refractive index at a low value, the optical members are preferably so arranged in combinations that the optical system comprises an overall optical path length composed of a total optical path lengths of the at least one crystalline optical member and of the at least one amorphous optical member, wherein the total optical path length of the at least one crystalline optical member is set at 25 % or less of the overall optical path length and the total optical path length of the at least one amorphous optical member belonging to the second quality is set at 50 % or more of the total optical path length. Preferably the average variation of refractive index Δn of the optical system is set at a value of $\Delta n \leq 2.0 \times 10^{-6} / \text{cm}$.

Brief Description of the Drawings

- Figure 1 is a schematic view showing a structure of an optical system for fabricating integrated circuits using a refractive optics to which the present invention is applied.
- Figure 2 is a schematic view showing a structure of an optical system for fabricating integrated circuits using a reflective optics to which the present invention is applied.
- Figure 3 is a graph showing an absorption band of fluoride of Sample C after laser irradiation in an example of the present invention.
- Figure 4 is a graph showing an absorption band of fluoride of Sample D after laser irradiation in a comparative example of the present invention.

Embodiments of the Invention

Examples of the present invention will be described referring to the accompanying drawings.

It is to be understood that, unless otherwise specified, the sizes, materials and shapes of constructing parts, relative configuration therebetween and the like are described without any sense of restricting the present invention thereto but exemplarily only.

Fig. 1 is a schematic view showing a structure of a photolithographic projection aligner using an ArF laser as a light source (for information of the fundamental structure of the projection aligner, see an article entitled "optical resolution technique in photolithography" in No. 182.0 plus E, the special issue on the leading edge of the lithographic technology 1). In the figure, 1 indicates an ArF excimer laser, 2 indicates a modified illumination means for formation of a pattern image on a wafer without any interference of diffracted light, which illumination means comprises a light source plane of, for example, quadrupole or ring illumination as viewed in sectional shape with a light-intercepting part in the central portion of the plane.

A numeral reference 3 indicates a condenser lens, which conducts an excimer laser beam emitted from the above-mentioned light source to a reticle, 4 indicates a mark (reticle), 5 indicates a refractive optical system, wherein, for example, a group of lenses with a positive refraction and another group of lenses with a negative refraction are combined in efforts to attain a narrower spectral band width and a pupil plane is formed in the refractive optical system so as to achieve an improved resolution. 6 indicates a wafer placed on a wafer stage 7 and a mask pattern depicted on the reticle 4 is projected on a wafer 6 to form an pattern image with the help of the refractive optical system 5.

In such a projection aligner, the ArF excimer laser light source can emit excimer laser light having a spectral band width as narrow as a width of 1.0 to 1.5 pm by arranging wavelength selecting elements, such as a prism, a diffraction grating and an etalon in a resonator of the laser as in a well known manner (see Optical and Quantum Electronics, Vol. 25 (1993) pp. 293 to 310).

The refractive optical system 5 comprises a group of condenser lenses 5a mounted in the closest position to a plane of a wafer, a group of lenses 5b mounted in the vicinity of the pupil plane, on which pupil plane a secondary light source is formed, said secondary light source being an image of the light source. Accordingly, if the light source image is formed in a dispersed manner in the pupil plane, local concentration of light energy is created and it can be

one of causes for breakage of not only a portion of the wafer side, but also a portion of the entire optical system.

On the reticle side of the optical system, operational conditions are milder than those on the wafer side, since an energy density is less by a factor of the second order of an imaging magnification.

In this example, such points as above-mentioned are considered. That is, it is reasonable that an energy density is determined by a magnification to an area of a pupil plane, wherein, according to a reference article, a size of the pupil plane of an ArF excimer laser is in the range of 30 to 50 mm in diameter.

Provided that a reticle sensitivity is, for example, in the range of 20 to 50 mJ and a photoresist film is exposed to 20 to 30 pulse laser irradiation, an energy density per pulse on the pupil plane is 0.6 to 1.7 mJ/cm². An energy density per pulse in the lenses located in the closest position to the surface of the wafer is, in practice, estimated to be in the range of 75 to 90 % of the above energy density, that is, in the range of 0.4 to 1.5 mJ/cm², even when it is assumed that, to be exact, there is a difference between energy densities on an image-forming plane and the pupil plane and the energy density on the wafer plane is a little larger than on the pupil plane. An energy density on the pupil plane seems to be less than the range of 0.4 to 1.5 mJ/cm² by a small difference.

While the refractive optical system is constructed with a combination of a group of lenses having a positive refraction and a group of lenses having a negative refraction for a improved resolution (see, for example, GB-A 2,153,543). In this case, removal of aberrations of the groups of lenses is required at a great extent and, for the purpose, magnifications of enlargement or reduction of respective lenses incorporated in the groups are properly selected in moderate ranges. In consideration of such circumstances, an energy density in a group of lenses in a position next to the closest position to the wafer side or pupil plane is estimated to be in the range of about one third of the above-mentioned range of 0.4 to 1.5 mJ/cm², that is, in the range of 0.1 to 0.4 mJ/cm².

An energy density per pulse in almost all the other groups of lenses, including lenses on the light source side is ≤ 0.1 mJ/cm².

In the above conditions of energy densities per pulse, a resolution of the entire optical system can be improved by attaching much importance to an optical transmittance rather than to

durability for a group of lenses having an energy density per pulse $e \leq 0.1 \text{ mJ/cm}^2$ among groups of lenses on the wafer side.

Therefore, in the case of synthetic quartz glass constituting an light source side optical members at $e \leq 0.1 \text{ mJ/cm}^2$ in this embodiment, while a hydrogen molecule concentration C_{H_2} is set at a value as low as in the range of $1 \times 10^{17} \leq C_{H_2} \leq 5 \times 10^{18} \text{ molecules/cm}^3$, and a refractive index (Δn) and a birefringence are set at respective values as of high quality as $\leq 1 \times 10^{-6}$ and $\leq 1.0 \text{ nm/cm}$, a transmittance of light at a 193 nm, which is a wavelength of a ArF laser, is set at a value as mild as 99.5 % or more.

Groups of lenses in the vicinity of the pupil plane and lenses in the closest position to the wafer whose energy density per pulse e is $\geq 0.4 \text{ mJ/cm}^2$ are attached importance to its durability so that durability of the entire optical system may be improved.

In the case of an optical member in the example, while an optical member, such as a lens, at $0.4 \leq e$, is made of single crystal fluorite and a refractive index (Δn) and a birefringence thereof are respectively set at values as mild as $\leq 3 \times 10^{-6}$ and $\leq 2.0 \text{ nm/cm}$ in order to achieve easy manufacture, light transmittance at 193 nm of a wavelength of ArF laser light is maintained at 99.8 % or more.

For optical members such as lenses, which are disposed in a position next to lenses at a high energy density per pulse of receiving light, and which is located in a position at an energy density per pulse e of received light in the range of $0.1 < e < 0.4 \text{ mJ/cm}^2$ between the above-mentioned ranges, a concentration of hydrogen molecules C_{H_2} is moderately set in the range of $5 \times 10^{17} \leq C_{H_2} \leq 5 \times 10^{18} \text{ molecules/cm}^3$, a distribution of refractive index (Δn) and birefringence are respectively set at values as mild as $\leq 2 \times 10^{-6}$ and $\leq 1.0 \text{ nm/cm}$ and a transmittance at 193 nm, which is a wavelength of ArF laser light, is set at 99.5 % or more, which is a value a little milder so as to make manufacture of the optical system easier.

It is preferred that groups of optical members having different optical properties are arranged in an optical system in such a combination that a total length of optical path through optical members under $0.4 \leq e \leq 1.5 \text{ mJ/cm}^2$ is equal to or less than 25 % of the total length through the entire optical system and a total length of optical path through optical members under $0.1 < e < 0.4 \text{ mJ/cm}^2$ is equal to or less than 25 % of the total length through the entire optical system in order to attain high transmittance through the entire optical system, while durability is secured, as described later in examples.

When a material of lenses constituting the optical system using refractive optics is considered, how a degree of deterioration of a lens is severe has to be determined in reference to the diameter of a lens. According to the reference article already referred in this specification, a size of a pupil plane of an ArF laser is in the range of 30 to 50 mm in diameter and it is reasonable that a magnification to the area as a divisor is adopted for a normalization.

A diameter of a lens in a close position to a pupil plane or a wafer surface receiving ArF excimer laser light of an energy density of $0.4 \leq \epsilon$ (mJ/cm²), more particularly of $0.4 \leq \epsilon \leq 1.5$ mJ/cm² is on the order of 80 mm in diameter as the maximum, if it is considered that the maximum size of a pupil is 50 mm in diameter and a used area of the lens for receiving the light is 80 % of the actual area. It is reasonably estimated from the above discussion that a lens diameter at an energy density of $0.4 \leq \epsilon \leq 1.5$ mJ/cm² of ArF laser light is about 80 mm or less.

According to a similar calculation to the above, in the case of a lens or the like at the energy density ϵ of $0.1 < \epsilon < 1$ mJ/cm² a magnification to a pupil plane area is on the order of 2 to 3 and thus a diameter of the lens corresponds to 80 to 100 mm in diameter.

In the case of a lens having a larger diameter than this (100 mm in diameter), an energy density in the lens is naturally a value as small as $\epsilon \leq 0.1$ mJ/cm².

In this case, too, it is preferable to set so that a total length of optical path through optical members, such as lenses and the like, equal to or less than 80 mm in diameter is 20 % or less of the total length of optical path of the entire optical system and that of optical members from 80 mm to 100 mm in diameter is 25 % or less.

The present invention may be applicable to a projection aligner using reflective optics in addition to the projection aligner using refractive optics shown in Fig. 1.

Fig. 2 is a schematic diagram showing a configuration of lenses and the like of an optical system using reflective optics, in which the aligner uses a beam splitter of a prism type in order to attain a high resolution (for information of the fundamental structure of the projection aligner, see an article entitled "optical resolution technique in photolithography" in No. 182.0 plus E, the special issue on the leading edge of the lithographic technology 1). Simply described, a beam is emitted from a light source 11 and the beam passes firstly through a first group of lenses 12, secondly through the beam splitter 13, thirdly through a second group of lenses 14 and then reaches a mirror 15. The beam is deflected at the mirror 15 and

condensed with a third group of lenses 16. Thereafter, a recticle 17 is scanned by the condensed beam and after scanning the reflected beam passes back again through the third group of lenses 16, reaches the mirror 15 to be reflected and again passes through the second group of lenses 14 to reach the beam splitter 13. The beam is at this time deflected in the beam splitter 13 and passes through a fourth group of lenses 19 to form a pattern image of integrated circuits on a wafer 18, which image results in a resist pattern after activation of a photosensitive resist applied on the wafer and a treatment in a developer solution.

In such a projection aligner, as well, the ArF excimer laser light source can emit excimer laser light having a spectral band width as narrow as a width of 1.0 to 1.5 pm by arranging wavelength selecting elements, such as a prism, a diffraction grating and an etalon in a resonator of the laser as in a well known manner.

Lenses made of single crystal fluoride are used as the fourth group of lenses 19 which are in the closest position to the wafer after the splitter 13 along the beam direction, since the fourth group of lenses 19 is under a condition at an energy density ϵ of $0.4 \leq \epsilon \leq 1.5 \text{ mJ/cm}^2$ of the beam, which is the maximum intensity of the optical system and a refractive index (Δn) and birefringence are respectively set at values as mild as $\leq 3 \times 10^{-6}$ and $\leq 2.0 \text{ nm/cm}$ in order to make fabrication easier and a transmittance at 193 nm, which is a wavelength of ArF laser light, is set at 99.8 % or more.

In the projection aligner, it is only required that the third group of lenses 16 has a hydrogen molecule concentration C_{H_2} in the range of $5 \times 10^{17} \leq C_{H_2} \leq 5 \times 10^{18} \text{ molecules/cm}^3$, a distribution of refractive index Δn as mild as $\leq 2 \times 10^{-4}$ and a birefringence as mild as $\leq 1.0 \text{ nm/cm}$, since it is estimated that the beam with an estimated energy density per pulse ϵ in the range $0.1 < \epsilon < 0.4 \text{ mJ/cm}^2$ passes through the recticle 17 side portion of the bulk of the third group of lenses 16, which estimation is based on a function that the beam is condensed by the third group of lenses 17 and then used for scanning the surface of the recticle 17. In other optical members of the optical system, such as the other lenses, mirror and beam splitter of a prism type, especially in the optical members close to the light source side thereof, a hydrogen molecule concentration C_{H_2} is set to be in the range of $1 \times 10^{17} \leq C_{H_2} \leq 5 \times 10^{18} \text{ molecules/cm}^3$, a distribution of refractive index Δn is set to be as of high quality as $\leq 1 \times 10^{-6}$ and a birefringence is set to be also as of high quality as $\leq 1.00 \text{ nm/cm}$, since such optical members are only affected by the beam with an energy density per pulse ϵ as low as $\epsilon \leq 0.1 \text{ mJ/cm}^2$.

In the embodiment, a combination of diameters of groups of lenses is set, as described above, such that a total length of optical path through the fourth group of lenses 19, whose diameters are set at 80 mm or less, is 25 % or less of the total length of optical path of the entire optical system and a total length of optical path through the third group of lenses, whose diameters are set in the range of 80 to 100 mm, is 25 % or less of the total length of optical path of the entire optical system, whereby it is estimated that a transmittance through the entire optical system can be achieved at 99.8 % or more, while durability thereof is secured.

Examples

Long term stability of optical properties in actual conditions was simulated by an acceleration test conducted in severer conditions on quartz glass optical members, such as a lens, mirror and prism, which were selected from an optical system incorporated in each of the projection aligners depicted in Figs. 1 and 2, since a long term stability test on each of projection aligners depicted in Figs. 1 and 2 takes a long time, if tested in actual operational conditions.

A progress speed of a damage by irradiation of laser light generally increases in proportion to the second power of an energy density of an irradiated excimer laser beam as in the teaching of an article printed in Japanese authored by Akira FUJINOKI with a title of "Quartz Glass for the Excimer Laser Use" appeared in "Optics", Vol. 23, No. 10, which is referred to "reference article 1." The acceleration test was conducted on the basis of the acceleration effect on the damage progress speed in the teaching.

First of all, description on optical materials used will be described.

Silicon tetrachloride was hydrolyzed in an oxygen/hydrogen flame and silica formed was further deposited on a rotating substrate to produce a quartz glass ingot, which is called DQ method.

The produced quartz glass ingot had OH groups at a concentration in the range of 800 to 1000 ppm and hydrogen molecules at a concentration of 5×10^{15} molecules/cm³. It received a homogenizing treatment comprising heating at 1150 °C for 40 hours and gradual cooling by a method disclosed in EP-A1 873 888 in order to remove strains in the bulk.

Optical properties were measured on the homogeneous quartz glass obtained. According to the measurements, it was found that it had no striae in three directions, a very good

homogeneity in refractive index distribution Δn of 1×10^{-6} was measured by an interferometer (ZYGO MARK IV) and a birefringence of 1 nm/cm or less was measured by a cross Nicols bi-refringences analyzer.

Such optical quartz glass meets requirements for optical properties of quartz glass used as material of optical members incorporated in an excimer laser stepper, which requirements are described in an article printed in Japanese with a title of "Quartz Glass for a Stepper", in New Glass, Vol. 6, No. 2 (1989) pp. 191-196. A projection aligner for semiconductor use having an ArF excimer laser as a light source can be constructed with optical members made of such optical quartz glass because of the quartz glass meeting the requirements.

The quartz glass thus produced was measured on a hydrogen molecule concentration included therein by a laser Raman spectroscopic analysis and the concentration was found to be 5×10^{17} molecules/cm³ (a specimen used for the measurement is hereinafter called Sample A).

A hydrogen molecule concentration was measured by a Raman spectrophotometer. The Raman spectrophotometer used in the measurements was a Raman spectrophotometer NR 1100 made by Nihon Bunko Kogyo K.K. and a photon counting method was adopted, wherein an Ar laser with an output of 700 mW at an excitation wavelength of 488 nm and a photon multiplier R943-D2 made by Hamamatsu photonics K.K. were used. A measurement was conducted by conversion to a hydrogen molecule concentration of a ratio of integrated intensities between a scattering band of SiO₂ at a wave number of 800 cm⁻¹ and a scattering band of hydrogen in a range of 4135 to 4140 cm⁻¹ in wave number observed in a Raman scattering spectrum, wherein a conversion constant was 1.22×10^{21} and, therefore,
 $C_{H_2} = \text{Integral intensity of SiO}_2 / \text{Integral intensity of Hydrogen times } 1.22 \times 10^{21}$, said constant being reported in Zhurnal Pri-Kladnoi Spektroskopii, Vol. 46, No. 6, pp. 987-991, June 1987.

The above quartz glass was cut to prepare a specimen having a size of 60 mm in diameter and 20 mm in thickness. The specimen was oxidized in atmospheric air at 1000 °C for 20 hours and the oxidized specimen was subjected to a hydrogen doping treatment in a high pressure hydrogen atmosphere at 0.8 MPa (8 kgf/cm²) at 600 °C for 1000 hours. The specimen thus treated was measured on a distribution of refractive index Δn , a birefringence and a hydrogen molecule concentration C_{H_2} , which were respectively 2×10^{-6} , 2 nm/cm and 4×10^{18} molecules/cm³ (the specimen is hereinafter called Sample B). On the other hand, a high purity optical use fluoride having dimensions of 60 mm in diameter x 20 mm in thickness of a UV grade article (for example, CaF₂/UV grade, Optron CaF₂/UV grade and the like

manufactured by Ohyo Kohken Co.) is prepared and measurements on layer characteristics were conducted.

The measurements were conducted with ArF laser light having a narrowed spectral band width of 1.0 to 1.5 pm and a change in transmittance was measured under an irradiation condition of an energy density per pulse $50 \text{ mJ/cm}^2 \cdot \text{p}$, 300 Hz and 10^6 shots of the light.

It was found that even in fluoride of the same UV grade, while some had a small absorption at 200 nm, but large absorptions at 320 nm and 380 nm, others had none of the absorptions. As shown in Fig. 3, on Sample C, a transmittance after the irradiation was measured as a good value of 99.0 % at 193 nm, but on Sample D, very large absorption bands at 250 nm and 370 nm were appeared and a transmittance was 95.3 % at 193 nm.

Homogeneities of refractive index Δn of Samples C, D are both 2×10^{-6} or less and birefringences are both 2 nm or less. Transmittance at 193 nm before laser irradiation was a good value of 99.8 %.

An estimation of a lifetime of an optical system constituting an projection aligner was carried out using the samples A to D by experiments.

In the experiments, changes in optical properties, particularly changes in transmittance and in refractive index at 193 nm are measured as acceleration tests in which ArF excimer laser light is irradiated on the samples A to D in conditions at an energy density of $50 \text{ mJ/cm}^2 \cdot \text{p}$ and 300 Hz and for 1×10^6 pulses.

The above mentioned conditions correspond to an acceleration test with a factor of $(100/\epsilon)^2$, where an energy density of laser light transmitted through an optical member in the actual working condition is $\epsilon \text{ mJ/cm}^2$, as shown in the reference article 1.

The results are shown in Table 1. An assumed energy density appeared in the table indicates a conceived energy density which is actually to be used in an optical member for estimation and estimated values for changes in transmittance and refractive index are those obtainable in conditions for 5×10^{10} shots at the conceived energy density.

Table 1

Samples	Decrease in Transmittance	Change in Refractive Index	Assumed Energy Density	Estimation of Change in Transmittance	Estimation of Change in Refractive Index
A	2.9%	2.5×10^{-5}	0,1	99.4%	5.0×10^{-7}
			0,4	91.0%	8.0×10^{-6}
			0,8	68.7%	3.2×10^{-5}
B	1.0%	5.6×10^{-7}	0,4	96.8%	2.1×10^{-6}
			0,6	87.9%	8.4×10^{-6}
C	1.0%	0	0,8	98.9%	0
D	8.3%	0	0,6	86.7%	0

Combinations in which a high transmittance is kept and a stability of refractive index is maintained over a long time in use were investigated in the cases of optical systems for reducing an image, said combinations of optical members being considered from the above mentioned experiments. The results are shown in Table 2, described below:

Table 2

	$0.1 \geq e$	$0.1 < e < 0.4$	$e \geq 0.4$	Overall Transmittance %/cm	Average Change in Refractive Index	Overall Appraisal
1	A	A	A	88.7	1.0×10^{-5}	X
2	A	A	B	94.3	4.3×10^{-6}	X
3	A	A	C	97.1	2.2×10^{-6}	Δ
4	A	B	B	95.8	2.8×10^{-6}	X
5	A	B	C	98.6	1.3×10^{-6}	O
6	A	B	D	95.6	1.0×10^{-6}	X

As can be seen from the table 2, when a combination of [A + B + C] in No. 5 is selected in the respective cases of small $0.1 \geq e$, medium $0.1 < e < 0.4$ and large $0.4 \leq e$, an overall average

transmittance and average change in refractive index are respectively 98.6 %/cm and 1.3×10^{-6} /cm, which satisfy requirements for standard values.

When a combination of [A + A + C] in No. 3 is selected, an overall transmittance and average change in refractive index are respectively 97.1 % and 2.2×10^{-6} /cm, any of which is outside the requirements for standard values, but it can be said that they almost satisfy the requirements. Especially in an actual image forming optical system, since laser light densities at which laser light is transmitted through lenses are different according to a design of the optical system, there is the case where even a combination of [A + A + C] can be endurable in a practical sense.

While No. 6 is a combination of a plurality of qualities of synthetic quartz glass [A + B] and fluorite D, that is a combination of [A + B + D], an overall transmittance is 95.6 %/cm, which is outside a requirement for a standard value. The reason why is that in the sample D shown in Fig. 4, very strong absorption bands appear at 250 nm and 370 nm and a transmittance at 193 nm is 95.3 %.

Therefore it is required that an average transmittance of the entire optical system is achieved to be about 98.0 %/cm or more.

From the simulation experiments, in order to suppress reduction in a transmittance caused by irradiation of laser light at a tolerable level, it is found to be a need that a total thickness of synthetic quartz glass as optical members at an energy density per pulse of 0.1 mJ/cm^2 of laser light is at least 50 % or more of a total length of optical path through the entire optical system and in addition, a total length of optical path through fluorite optical members disposed in a region at an energy density is $0.4 \leq \epsilon$ of light is 25 % or less of the total length of optical path of the entire optical system.

For calculation, it is assumed that optical path lengths are respectively are set at about 2 (50%) : 1 (25%) : 1 (25%) in ratio for optical path lengths at energy densities, small, medium and large.

From the experiments, a projection aligner comprising an optical system constructed from synthetic quartz glass optical members and fluorite optical members is expected to have a long lifetime with sufficient stability of optical properties in an actual operation.

WO 98/43135

PCT/EP98/01692

- 18 -

Effect of the invention

As has been described, according to the present invention, even a projection aligner with ArF excimer laser as light source using an optical system made of quartz glass containing hydrogen can be produced as the projection aligner with durability and no deterioration of optical properties at a low cost and with ease as a whole of the optical system.

**OPTICAL SYSTEM
FOR INTEGRATED CIRCUIT FABRICATION**

Claims

1. Optical system for integrated circuit fabrication, in which an integrated circuit pattern image is projected on a wafer using an excimer laser emitting ultraviolet laser light of a short wavelength, comprising at least one crystalline optical member made of a single crystal fluorite and at least one amorphous optical member made of synthetic quartz glass, wherein said crystalline optical member is disposed in a first position closest to an exposing surface of a wafer and/or a pupil plane, which is a position through which the laser light is transmitted at a relatively high light energy density s (mJ/cm^2), and said amorphous optical member is disposed in a second position remote from the exposing surface of a wafer and/or the pupil plane, which is a position through which the laser light is transmitted at a relatively low light energy density s (mJ/cm^2) and whereby the amorphous optical member is made of quartz glass having a hydrogen molecule concentration in the range of 1×10^{17} molecules/ cm^3 to 5×10^{18} molecules/ cm^3 .
2. Optical system according to claim 1, wherein after irradiation with a pulsed laser light having a wavelength of 193 nm at an energy density per pulse of $50 \text{ mJ}/\text{cm}^2$ and at a pulse count of 1×10^6 the crystalline optical member has an internal transmittance of 98 %/cm or more.
3. Optical system according to claim 1 or 2, wherein the birefringence of the amorphous optical member is lower than the birefringence of the crystalline optical member.

4. Optical system according to one of the claims 1 to 3, wherein the crystalline optical member is made from a single crystal fluore which has a homogeneity of refractive index Δn of $3 \times 10^{-6}/\text{cm}$ or less and a birefringence of 2 nm/cm or less, and the amorphous optical member is made from a synthetic quartz glass which has a homogeneity of refractive index Δn of $2 \times 10^{-6}/\text{cm}$ or less and a birefringence of 1 nm/cm or less.
5. Optical system according to claim 4, wherein it uses refractive optics comprising several amorphous optical members made of at least a first and a second quality of synthetic quartz glass, whereby the first quality has a hydrogen molecule concentration of at least 5×10^{17} molecules/cm³, and the second quality has a hydrogen molecule concentration of at least 1×10^{17} molecules/cm³.
6. Optical system according to one of the claims 1 to 5, wherein the excimer laser is an ArF excimer laser emitting laser light having an oscillating wavelength width of 1.5 pm or less.
7. Optical system according to the claims 5 and 6, wherein for the ArF excimer laser light having a wavelength of 193 nm the average transmittance of the optical system as a whole is about 98.0 %/cm or more, the transmittance of the at least one amorphous optical member is 99.5 %/cm or more and the transmittance for the crystalline optical member is 99.8 %/cm or more, whereby at least one amorphous optical member belonging to the second quality is disposed in a region through which the laser light is transmitted at an energy density of $e \leq 0.1$ mJ/cm², and at least one amorphous optical member belonging to the first quality is disposed in a region, through which the laser light is transmitted at an energy density of $0.1 < e < 0.4$ mJ/cm², and the at least one crystalline optical member is disposed in a region, through which the laser light is transmitted at an energy density of $e \geq 0.4$ mJ/cm².
8. Optical system according to claim 7, wherein the optical system comprises an overall optical path length composed of a total optical path lengths of the at least one crystalline optical member and of the at least one amorphous optical member, wherein the total optical path length of the at least one crystalline optical member is set at 25 % or less of the overall optical path length and the total optical path length of the at least one amorphous optical member belonging to the second quality is set at 50 % or more of the total optical path length.

9. Optical system according to claim 8, wherein the average variation of refractive index Δn of the optical system is set at a value of $\Delta n \leq 2.0 \times 10^{-6}/\text{cm}$.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau


INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6: G03F 7/20		(11) International Publication Number: WO 98/43135
A1		(43) International Publication Date: 1 October 1998 (01.10.98)
(21) International Application Number: PCT/EP98/01692		(81) Designated States: US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.
(22) International Filing Date: 23 March 1998 (23.03.98)		
(30) Priority Data:		
9/90232	25 March 1997 (25.03.97) JP	
9/90235	25 March 1997 (25.03.97) JP	
(71) Applicants (for all designated States except US): HERAEUS QUARZGLAS GMBH [DE/DE]; Quarzstrasse, D-63450 Hanau (DE). SHIN-ITSU QUARTZ PRODUCTS CO., LTD. [JP/JP]; 22-2, Nishi-Shinjuku 1-chome, Shinjuku-ku (JP).		
(72) Inventors; and		
(75) Inventors/Applicants (for US only): FUJINOKI, Akira [JP/JP]; 1-6-12, Midorigaoka-nishi, Koriyama-shi (JP). NISHIMURA, Hiroyuki [JP/JP]; 3-46, Hidenoyama, Asaka-machi, Koriyama-shi (JP).		
(74) Agent: STAUDT, Armin; Heraeus Quarzglas GmbH, Schutzrechte, Quarzstrasse, D-63450 Hanau (DE).		

(54) Title: OPTICAL SYSTEM FOR INTEGRATED CIRCUIT FABRICATION

(57) Abstract

Object: to provide a projection aligner with ArF excimer laser as light source using an optical system made of quartz glass containing hydrogen producible with durability and no deterioration of optical properties at a low cost and with ease as a whole of the optical system. Constitution: in order to improve resistance to laser light and secure high transmittance, as a whole, in an optical system, the optical system comprises optical members made of synthetic quartz glass and fluoride, wherein: an optical member disposed in a position, through which laser light is transmitted at a high light energy density, is made of single crystal fluoride; and an optical member in a position, through which laser light is transmitted at a low light energy density, is made of synthetic quartz glass containing approximately such a hydrogen molecule concentration as can be doped under atmospheric pressure.




FOR THE PURPOSES OF INFORMATION ONLY


Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NI	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark			SG	Singapore		
EE	Estonia						


[Fig. 1]




[Fig. 2]



[Fig. 3]



[Fig. 4]



INTERNATIONAL SEARCH REPORT

International Application No.
PCT/EP 98/01692

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 G03F7/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 G03F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 96, no. 7, 31 July 1996 & JP 08 078319 A (NIKON CORP), 22 March 1996 cited in the application see abstract	1
A	EP 0 483 752 A (SHIN-ETZU QUARTZ PRODUCTS) 6 May 1992 cited in the application see the whole document	1
A	EP 0 401 845 A (SHIN-ETZU QUARTZ PRODUCTS) 12 December 1990 cited in the application see the whole document	1
-/-		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document published on or after the international filing date

"L" document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in context with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"Z" document member of the same patent family

Date of the actual completion of the international search

5 August 1998

Date of mailing of the international search report

17/08/1998

Name and mailing address of the ISA

European Patent Office, P.O. 5418 Patentplan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl
Fax: (+31-70) 340-2016

Authorized officer

Sarneel, A

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 98/01692

B. (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 96, no. 5, 31 May 1996 & JP 08 005801 A (NIKON CORP), 12 January 1996 see abstract	1
A	PATENT ABSTRACTS OF JAPAN vol. 10, no. 319 (E-450), 30 October 1986 & JP 61 129828 A (CANON INC.), 17 June 1986 see abstract	1
A	M. KAMEYAMA ET AL.; "The way to one-half micrometer photolithography" OPTICAL ENGINEERING, vol. 26, no. 4, April 1987, pages 304-310, XP002073667 BELLINGHAM US see paragraph 2.3	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.

PCT/EP 98/01692

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 483752 A	06-05-1992	JP 4164833 A	10-06-1992
		JP 8025764 B	13-03-1996
		JP 4164834 A	10-05-1992
		JP 8025765 B	13-03-1996
		JP 4224130 A	13-08-1992
		JP 8000711 B	10-01-1996
		JP 4224131 A	13-08-1992
		JP 8000712 B	10-01-1996
		AT 135669 T	15-04-1996
		DE 69118101 D	25-04-1996
		DE 69118101 T	19-09-1996
		US 5410428 A	25-04-1995
		JP 5043267 A	23-02-1993
EP 401845 A	12-12-1990	AT 116448 T	15-01-1995
		DE 69015453 D	09-02-1995
		DE 69015453 T	01-06-1995
		JP 3088742 A	15-04-1991
		JP 6053593 B	20-07-1994
		US 5086352 A	04-02-1992
		US 5325230 A	28-06-1994
		JP 3109233 A	09-05-1991
		JP 6027013 B	13-04-1994
		JP 3101282 A	26-04-1991
		JP 6048734 B	22-06-1994
		JP 1898031 C	23-01-1995
		JP 3086743 A	15-04-1991
		JP 6027014 B	13-04-1994